



**CASA**

QUALITY: Corrected Grain

AVERAGE HIDE SIZE: 5.0m2

Thickness: 1.0-1.2mm

Casa is a corrected grain leather in which the natural grain has been removed and replaced with an artificial embossing and is aniline drum dyed. Due to this process the leather is durable and cutting yield is excellent, therefore providing a great economical leather.

Characteristic	Test Method	Test Results	
COLOUR FASTNESS TO RUBBING	EN ISO 11640 EN ISO 11641	Dry Wet Perspiration	4-5 4-5 4-5
LIGHT FASTNESS	EN ISO 105-B02	5	
FINISH ADHESION	EN ISO 11644	8.7 N/10mm	
pH	EN ISO 4045 (1977)	3.45	
FLEXING ENDURANCE	EN ISO 5402	50,000 cycles (no finish damage cracks)	
TEAR STRENGTH	EN ISO 3377-1	48.7N	
FLAME RESISTANCE	AS 1530.3 Report #: 7-539056-CN	Ignitability Spread of Flame Heat Evolved Smoke Developed	16 0 2 4
	AS 3837 Report #: 7-557463 - BN	Pass	
	BS5852:1979	Pass	
ENVIRONMENTAL	<ul style="list-style-type: none"> <li>All wastewater is cleaned in a biological treatment plant, recycled and reused. No PCP, Chrome vi, CADMIUM, FORMALDEHYDE or AZO – Col Dyes are used in the tanning process. All dyes and pigments (finishes) are solvent free ie <b>water based</b></li> <li>State of the art application technology optimizes the finishing process and greatly reduces the rate of airborne emissions.</li> <li>Regular inspections are conducted to ensure that quality and environmental standards are maintained at all times.</li> <li>Low VOC product.</li> </ul>		
CARE OF LEATHER	<ul style="list-style-type: none"> <li>Do not place leather in direct sunlight.</li> <li>Ensure a minimum of 80cm between furniture and heating source.</li> <li>Avoid contact of leather with sharp objects.</li> <li>Regularly clean and dust your leather with a clean dry cloth.</li> <li>Remove food spills immediately. Do not scrub hard.</li> <li>Avoid using harsh chemicals and / or cleaners that are oil or solvent based.</li> <li>Only clean leather with approved upholstery leather cleaners in accordance with the manufacturers instructions.</li> </ul>		

Pelle Leathers Division of Antac (Aust) Pty Ltd ABN 96 001 866 404

Unit 6, 2-6 Waltham Street Artarmon NSW 2064 . PO Box 380 Artarmon NSW 1570 AUSTRALIA.

Telephone: +61 2 9460 9222 . Facsimile: +61 2 9460 6599 .

Email: [sales@pelleleathers.com.au](mailto:sales@pelleleathers.com.au) [www.pelleleathers.com.au](http://www.pelleleathers.com.au)