

pelle leathers

SAFARI

TYPE: Aniline leather AVERAGE HIDE SIZE: 5.5m2 Thickness: 1.4 – 1.6 mm

With a sumptuous sitting comfort and a soft hand, Safari displays all the characteristics of an aniline leather. The unique shrunken grain appearance enhances this beautiful leather.

Characteristic	Test Method	Test Results	
COLOUR FASTNESS TO RUBBING	EN ISO 11640 EN ISO 11640	Dry Wet	>3 >3
TEAR STRENGTH	DIN 53329A	> 20 N	
LIGHT FASTNESS	EN ISO 105-B02	3	
FLAME RESISTANCE	AS 1530.3 Report No. 7-539730-CN	Ignitability Spread of Flame Heat Evolved Smoke Developed	15 0 2 3
	EN 1021:1 & EN 1021:2 ISO8191:1 & ISO 8191:2	Pass	
ENVIRONMENTAL	<ul style="list-style-type: none"> All wastewater is cleaned in a biological treatment plant, recycled and reused. No PCP, Chrome VI, CADMIUM, FORMALDEHYDE or AZO – Col Dyes are used in the tanning process. All dyes and pigments (finishes) are solvent free ie. water based State of the art application technology optimizes the finishing process and greatly reduces the rate of airborne emissions. Regular inspections are conducted to ensure that quality and environmental standards are maintained at all times. Low VOC product. 		
CARE OF LEATHER	<ul style="list-style-type: none"> Do not place leather in direct sunlight. Ensure a minimum of 80cm between furniture and heating source. Avoid contact of leather with sharp objects. Regularly clean and dust your leather with a clean dry cloth. Remove food spills immediately. Do not scrub hard. Avoid using harsh chemicals or cleaners that are oil or solvent based. Only clean leather with approved upholstery leather cleaners in accordance with the manufacturer's instructions. 		

Pelle Leathers Division of Antac (Aust) Pty Ltd ABN 96 001 866 404

Unit 6, 2-6 Waltham Street Artarmon NSW 2064 . PO Box 380 Artarmon NSW 1570 AUSTRALIA.

Telephone: +61 2 9460 9222 . Facsimile: +61 2 9460 6599 .

Email: sales@pelleleathers.com.au www.pelleleathers.com.au